



China General Plastics Corporation CGPC Polymer Corporation

Head office

7F, 37, Ji-Hu Rd. Nei-Hu Dist., Taipei 114, Taiwan
Tel :886-2-2658-2158
Fax:886-2-2659-9515

Toufen Plant

571, Min-Tsu Rd. Toufen, Miaoli 351, Taiwan
Tel :886-37-623-391
Fax:886-37-613-326

Lin Yuan Plant

8, Shihua 2nd Rd. Lin Yuan, Kaohsiung 832, Taiwan
Tel :886-7-704-0988
Fax:886-7-641-7672

United States

CGPC America Corporation
11310 Harrel Street. Mira Loma, CA 91752-1408 USA
Tel :909-594-0800
Fax:909-594-0062(General)
909-594-0172(Customer Service)
Toll Free:800-243-2472

Web Sites

<http://www.cgpc.com.tw>
<http://www.cgpcamerica.com>



Properties

Grade	H-58	H-61	H-66	H-73	Test Method
K-Value	57~59	60~62	65~67	72~74	ISO 1628-2
Degree of Polymerization	700±50	800±50	1000±50	1350±50	--
Bulk Density (g/cc)	0.52~0.59	0.52~0.59	0.48~0.56	0.45~0.53	ISO 60
Volatiles(%)	≤0.3	≤0.3	≤0.3	≤0.3	ISO 1269
Particle Size (45 Mesh pass%)	≥99	≥99	≥99	≥99	Honeywell SRA-150
Foreign matters (grains/100g)	≤40	≤40	≤40	≤40	Visual Inspection
Residual VCM (ppm)	<1	<1	<1	<1	ISO 6401

Packages

25kg/Bag

H58/H61/H66 --17mt/20'

H-73 -- 14.6mt/20'

H58/H61/H66/H73---23mt/40'

1.1mt or 1.15mt/Jumbo bag


H58/H61/H66/H73--23mt/40' with palletized

H61/H66--22mt/40' with palletized

Applications

H-58

Injection moulding (Fitting), Blowing moulding (Bottle).



H-61

Injection moulding (Pipe fitting), Hollow-Vacuum forming (Bottle blowing) Rigid film, Shrinkable film.



H-66

Flexible and semi-rigid products for general purpose(PVC film, sheet, beach chair, venetian blind), Rigid pipe, Hose, Low temperature wire and cable.



H-73

High impact flexible products(PVC leather, film, furniture, shoes), High impact sheet, High voltage wire and cable.

