

Rigid Extrusion

Properties

Items / Test Method (ASTM)		General	Transparent IC tubes	Profile Extrusion	Pipes	Transparent Shinkable Film
Specific Gravity	D-792	1.42~1.46	1.34~1.36	1.48~1.54	1.42~1.44	1.33~1.35
Tensile Strength (kg/cm ²)	D-638	>500	>500	>340	>500	>480
Elongation (%)	D-638	>80	>50	>30	>80	>100
Impact Strength (kg-cm/cm ²)	D-256	>3.5	>4.5	>3.5	>3.5	>4.5

* Comply with RoHS.

Applications

General, Transparent IC Tubes, Profile Extrusion, Pipes, Transparent Shrinkable Film

