

Rigid Injection

Properties

Items / Test Method (ASTM)		General	Fittings	Valves	Case
Specific Gravity	D-792	1.33~1.35	1.39~1.41	1.34~1.37	1.39~1.41
Tensile Strength (kg/cm ²)	D-638	>360	>480	>450	>400
Elongation (%)	D-638	>75	>140	>100	>50
Impact Strength (kg-cm/cm ²)	D-256	>2	>6	>12	>10

* Comply with RoHS.

Applications

General, Fittings, Valves, Case

