

Bottle Molding

Properties

Items / Test Method (ASTM)		General	Cosmetic Bottles	Oil Bottles	High Impact
Specific Gravity	D-792	1.32~1.34	1.35~1.37	1.34~1.36	1.31~1.33
Tensile Strength (kg/cm ²)	D-638	>410	>440	>420	>400
Elongation (%)	D-638	>100	>100	>100	>100
Impact Strength (kg-cm/cm ²)	D-256	>30	>4	>10	>50

* Comply with RoHS.

Applications

General, Cosmetic Bottles, Oil Bottles, High Impact

