

試驗報告



報告編號：HV-16-04982X

頁數：1 OF 3

報告日期：2016年09月09日

華夏海灣塑膠股份有限公司
苗栗縣頭份鎮民族路571號

我們依照顧客的要求，根據顧客提供的產品敘述如下：

產品名稱： Q-BOX 板
產品顏色： 白色
製造廠商： 華夏海灣塑膠股份有限公司
備註： 除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製

我們依照顧客的要求，根據顧客送交之樣品進行試驗結果如下：

委託試驗要求：(依照顧客提供之測試規格進行試驗，詳細內容請參照附頁。)

防焰性

試驗結果：

—如附頁所示—

收件日期： 2016年08月25日

試驗日期： 2016年08月25日~2016年09月09日


報告簽署人

試驗報告



報告編號：HV-16-04982X

頁數：2 OF 3

報告日期：2016年09月09日

防焰性

試驗設備：

名稱	廠牌	型號
梅克爾燃燒試驗機	SUGA	FL-45MC

實驗室環境條件：

環境溫度：23±2°C
 相對濕度：65±5%RH

試驗方法：

CNS 7614(1994) 薄材料防焰性試驗法

試驗條件：

試驗程序：A 法
 樣品平均厚度：34.9 mm

試驗結果：

試驗項目	試驗結果	CNS7614(1994) 防焰一級規範值	CNS7614(1994) 防焰二級規範值	CNS7614(1994) 防焰三級規範值
火源加熱時間(sec)	10	-	-	-
餘焰時間(sec)	0.0	≤1	≤5	≤5
餘燼時間(sec)	0.0	≤60	≤60	≤60
炭化長度(cm)	4.4	≤5	≤10	≤15

試驗報告




報告編號：HV-16-04982X

頁數：3 OF 3

報告日期：2016年09月09日

試驗照片：



試驗樣品

---- o O o ----

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.